



MICROCUT® CCA

For high demands in microerosion

- Combines the best properties of cobracut® and microcut®, thereby providing reproducible results with best surface quality, even in case of very small energy impulses
- Due to its high tensile strength and minimal tolerance of the wire diameter particularly suited for precise fine contours

Technical data

Core	CuZn36
Coating	Zn treated
Tensile strength	1.000 MPa / 145,000 PSI
Elongation	1%
Color	Grey

Delivery program

Diameter [mm]	0,05	0,06	0,07	0,08	0,09	0,10
bedra4: 10.000 m	●	●				
bedra4: 20.000 m	●	●	●	●	●	●
bedra4: 30.000 m			●	●	●	●
bedra4: 60.000 m						●